

What is claimed is:

1. A coextruded, transparent, biaxially oriented polyester film comprising a base layer (B) and a heatsealable top layer (A) which is peelable from APET, the heatsealable and peelable top layer (A) consisting of
 - 70-97 % by weight of polyester and
 - 3-20 % by weight of a polyester-incompatible polymer (= anti-PET polymer)based on the mass of the top layer (A), and
 - the polyester being composed of 20-95 mol% of units which derive from at least one aromatic dicarboxylic acid and 5-80 mol% of units which derive from at least one aliphatic dicarboxylic acid, the sum of the dicarboxylic acid-derived molar percentages being 100, and
 - the layer thickness of the top layer (A) d_A being from 1.7 to 6.0 μm .
2. The sealable and peelable polyester film as claimed in claim 1, wherein the aliphatic dicarboxylic acids are selected from one or more of the following substances: pimelic acid, suberic acid, azelaic acid, sebacic acid, glutaric acid and adipic acid.
3. The sealable and peelable polyester film as claimed in claim 1 or 2, wherein the aromatic dicarboxylic acids are selected from one or more of the following substances: terephthalic acid, isophthalic acid and 2,6-naphthalenedicarboxylic acid.
4. The sealable and peelable polyester film as claimed

03/035 MFE

in one of claims 1 to 3, wherein the polyester of the top layer (A) comprises:

from 20 to 95 mol% of terephthalate,

from 0 to 25 mol% of isophthalate,

5 from 5 to 80 mol% of azelate,

from 0 to 50 mol% of sebacate,

from 0 to 50 mol% of adipate,

more than 30 mol% of ethylene,

10 based in each case on the total amount of dicarboxylate or the total amount of alkylene.

5. The sealable and peelable polyester film as claimed in one of claims 1 to 4, wherein the heatsealable and peelable top layer (A) has a sealing commencement
15 temperature (= minimum sealing temperature) with respect to the APET side of APET/CPET trays of not more than 165 °C.

20 6. The sealable and peelable polyester film as claimed in one of claims 1 to 5, wherein the heatsealable and peelable top layer (A) has a seal seam strength with respect to the APET side of APET/CPET trays of at least 1.5 N.

25 7. The sealable and peelable polyester film as claimed in one of claims 1 to 6, wherein the heatsealable and peelable top layer (A) with respect to the APET side of APET/CPET trays has a max. sealing temperature of 220 °C.

30 8. The sealable and peelable polyester film as claimed in one of claims 1 to 7, wherein the sealing temperature (in °C) and the peeling force (in N/15 mm) are correlated via the following equation:

03/035 MFE

$0.0035 \cdot \vartheta/^{\circ}\text{C} - 3.6 \leq \text{peeling force } F/N \text{ per } 15 \text{ mm} \leq 0.05 \cdot \vartheta/^{\circ}\text{C} - 2.5$

9. The sealable and peelable polyester film as claimed in one of claims 1 to 8, wherein the anti-PET polymer is selected from one or more of the following substances: polymers based on ethylene, propylene (PP), cycloolefins (CO), amides (PA) and styrene (PS).
10. The sealable and peelable polyester film as claimed in claim 9, wherein the anti-PET polymer is selected from one or more of the following substances: copolymers based on norbornene/ethylene and tetracyclododecene/ethylene.
11. The sealable and peelable polyester film as claimed in one of claims 1 to 10, wherein the polyester for the top layer (A) is produced from two polyesters I and II.
12. The sealable and peelable polyester film as claimed in claim 11, wherein the proportion of the polyester I in the top layer (A) is from 10 to 60 % by weight.
13. The sealable and peelable polyester film as claimed in claim 12, wherein the polyester I consists of one or more aromatic dicarboxylates and one or more aliphatic alkylenes.
14. The sealable and peelable polyester film as claimed in claim 11, wherein the proportion of polyester II in the top layer (A) is from 20 to 80 % by weight.
15. The sealable and peelable polyester film as claimed

in claim 14, wherein the polyester II consists of one or more aromatic dicarboxylates and also one or more aliphatic dicarboxylates and one or more aliphatic alkylenes.

5

16. The sealable and peelable polyester film as claimed in one of claims 11 to 15, wherein the glass transition temperature of polyester I is more than 50 °C.

10

17. The sealable and peelable polyester film as claimed in one of claims 11 to 16, wherein the glass transition temperature of polyester II is less than 20 °C.

15

18. The sealable and peelable polyester film as claimed in one of claims 1 to 17, wherein the distribution of the particle diameters of the particles has a degree of scatter which is described by a SPAN98 of ≤ 2.0 .

20

19. The sealable and peelable polyester film as claimed in one of claims 1 to 18, wherein the film has two layers and an AB structure.

25

20. The sealable and peelable polyester film as claimed in one of claims 1 to 18, wherein the film has three layers and an ABC structure.

30

21. A process for producing a sealable and peelable polyester film as claimed in claim 1, in which the polymers for the base layer (B) and the top layer (A) which is composed of a polyester which is composed of - 20-95 mol% of units which derive from at least one aromatic dicarboxylic acid and

03/035 MFE

- 5-80 mol% of units which derive from at least one aliphatic dicarboxylic acid,
and, where appropriate, the top layer (C) are fed to separate extruders, the melts are then shaped and layered on top of one another in a multilayer die to give flat melt films, then the multilayer film is drawn off with the aid of a chill roll and optionally further rolls, solidified and then biaxially stretch-oriented and heat-set, the biaxial stretching being carried out in succession, first longitudinally (in machine direction) and then transversely (at right angles to machine direction) that the longitudinal stretch is carried out at a temperature in the range from 60 to 130 °C and the transverse stretching in the range from 90 to 140 °C, and that the longitudinal stretching ratio is set within the range from 2.0:1 to 5.5:1 and the transverse stretching ratio within the range from 2.4:1 to 5.0:1.
22. The process as claimed in claim 21, in which the longitudinal stretching is carried out at a temperature in the range from 60 to 120 °C and the transverse stretching in the range from 90 to 140 °C and that the longitudinal stretching ratio is in the range from 2.0:1 to 5.0:1 and the transverse stretching in the range from 2.4:1 to 5.0:1.
23. The process as claimed in claim 21, in which the longitudinal stretching is carried out at a temperature in the range from 60 to 110 °C and the transverse stretching in the range from 90 to 140 °C and that the longitudinal stretching ratio is set within the range from 2.0:1 to 4.8:1 and the transverse stretching within the range from 2.4:1 to

03/035 MFE

5.0:1.

24. The use of a sealable polyester film as claimed in one of claims 1 to 20 as a lid film for covering APET/CPET trays.
- 5